

In the claims:

Please amend claims 1-11 and 25-26 as follows:

1. (Currently Amended) A polymerisable mixture comprising at least the following two components:

- (i) a liquid crystal monomer or pre-polymer having cross-linkable groups;
and
- (ii) a photo-orientable monomer or oligomer or polymer.

2. (Currently Amended) A mixture according to Claim 1, wherein the cross-linkable liquid crystal component [substance] (i) is present in an amount of 100 parts by weight, and the photo-orientable component [substance] (ii) is present in an amount of at least 0.1 part by weight.

3. (Currently Amended) A mixture according to Claim 2, wherein the photo-orientable component [substance] (ii) is present in an amount of at least 1 part by weight.

b1
4. (Currently Amended) A mixture according to Claim 2, wherein the photo-orientable component [substance] (ii) is present in an amount of at least 10 parts by weight.

5. (Currently Amended) A mixture according to Claim 1, wherein the photo-orientable component [substance] (ii) comprises molecules showing a cis-trans-isomerism.

6. (Currently Amended) A mixture according to Claim 5, wherein the photo-orientable component [substance] (ii) comprises a compound belonging to the group of azo dyes.

7. (Currently Amended) A mixture according to Claim 1, wherein the photo-orientable component [substance] (ii) comprises a linearly photo-polymerisable monomer or oligomer or polymer.

8. (Currently Amended) A mixture according to Claim 1, wherein the cross-linkable liquid crystal component [substance] (i) has a nematic phase.

9. (Currently Amended) A mixture according to Claim 1, wherein the cross-linkable liquid crystal component [substance] (i) has a cholesteric phase.

10. (Currently Amended) A mixture according to Claim 1, wherein the cross-linkable liquid crystal component [substance] (i) has a ferroelectric phase.

11. (Currently Amended) A mixture according to Claim 1, wherein the cross-linkable liquid crystal component [substance] (i) is or comprises acrylate or diacrylate.

12. (Previously Amended) A mixture according to Claim 1, further comprising chiral molecules.

13. (Previously Amended) A mixture according to Claim 1, further comprising dye molecules.

14. (Previously Amended) A mixture according to Claim 1, further comprising dichroic molecules.

15. (Previously Amended) A mixture according to Claim 1, further comprising fluorescent molecules.

16. (Previously Amended) A mixture according to Claim 1, which is dissolved in a solvent.

17. (Previously Amended) A presensitised film precursor, comprising a substrate carrying a layer of a mixture according to Claim 1.

18. (Previously Amended) A substrate having an electrically conductive surface which carries a layer of a mixture according to Claim 1.

19. (Previously Amended) An optical component comprising an at least partly polymerised layer of a mixture according to Claim 1.

20. (Original) An optical component according to Claim 19, wherein the layer is optically anisotropic.

21. (Previously Amended) An optical component according to Claim 19, wherein the layer is polymerised with a preferred orientation direction.

22. (Original) An optical component according to Claim 21, wherein the layer is polymerised with locally varying preferred orientation directions.

23. (Previously Amended) An optical component according to Claim 19, wherein the layer has the function of an orientation layer.

24. (Previously Amended) An optical component according to Claim 19, wherein the layer has the function of a retarder or an optical filter or a polarizer or a polarised light emitter.

25. (Currently Amended) An optical component according to Claim 19, wherein the layer has the function of an orientation layer as well as the function of a retarder, [or] an optical filter, [or] a polarizer, or a polarised light emitter.

26. (Currently Amended) A method of making an at least partly polymerised, optically anisotropic layer of a mixture according to Claim 1, comprising

- (a) exposing the mixture to linearly polarised light while maintaining such conditions that the polymerisation or cross-linking of component [substance] (i) is essentially inhibited, whereby at least some of the molecules of the component [substance] (ii) are photo-oriented; and
- (b) allowing component [substance] (i) to adopt the imposed orientation(s) and exposing the mixture to light, whereby at least some of the molecules of the component [substance] (i) are polymerised or cross-linked.

27. (Original) A method according to Claim 26, wherein during step (a) the mixture is maintained in its isotropic phase.

28. (Previously Amended) A method according to Claim 26, wherein during step (a) the mixture is exposed to light of different directions of polarisation in different parts.

29. (Previously Amended) An optical component made by a method according to Claim 26.
